



PRODUCT INFORMATION



MC262 OMNI SV 2.1 Clear

Background

OmnTM SV MC262 2.1 Clear is a fast-drying, two component, acrylic urethane clear, that outperforms alternative value-priced clearcoats. This versatile urethane clear can be flattened and used as a specialty coating for low gloss interior and exterior applications. Inside and out, this economical coating is ready to tackle a variety of projects.

MC262 OMNI SV 2.1 Clear

Primer

MH262 2.1 Clear

Hardener

MH266 Spot Repair Hardener for MC262

MH267 Overall Hardener for MC262

Compatible Surfaces

MBC / MBP Basecoats

MTK Acrylic Urethane

MAE/MH101/MH202 Catalyzed Acrylic Enamel

Preparation

Refer to the information bulletin for MBC, MBP, MTK, or MAE/MH101/MH202 for preparation of the color.

The maximum time to clearcoat is 24 hours for MBC / MBP color and 1 week for MTK color or MAE/MH101/MH202

Mixing

Ratios



MC262
4

MH266 or MH267
1



1 - 1.5 hours at 70° (21°C) w/MH266
2 - 2.5 hours at 70° (21°C) w/MH267

Additives

M148 Flattening Agent*

Flat

Add 70 oz./RTS gal.

Eggshell

Add 60 oz./RTS gal.

Semi-gloss

Add 40 oz./RTS gal.

MR189 Retarder**

Add 10% / RTS quart

MX194 Fisheye Eliminator

Add ½ oz. / RTS quart

* Clear may be flattened and used as a specialty coating for low gloss interior and exterior applications.

**Addition of retarder may result in a non-compliant ready to spray VOC. Verify local regulations prior to use.

Application

Coats



2 – 3 coats

Air pressure



HVLP 8 – 10 psi at the air cap
Conventional 50 – 60 psi at the gun

Gun setup

1.3 - 1.6 mm or equivalent

Dry Times

Between coats



5 – 10 minutes at 70°F (21°C)

Air dry



	W / MH266 (Spot Repair)	W / MH266 (Spot Repair)
Dust:	10 – 15 minutes	20 – 30 minutes
Tack:	40 – 60 minutes	50 – 70 minutes
Tape:	1 – 3 hours	2 – 4 hours

16 hours at 70°F (21°C) to polish and put into service

Force dry

30 minutes at 140°F (60°C), allow 2 hours to polish and put into service

IR

12 – 15 minutes

Clean Up

Clean spray guns, gun cups, storage pots, etc., thoroughly with MR Reducer, General Purpose Solvent or other appropriate clean up solvent after each use.

Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Properties

VOC less water / less exempt

Package	2.49 lbs. / gal. / 298 gm/l
Applied (4:1)	2.08 lbs. / gal. / 249 gm/l
Applied (4:1+10% MR189)	2.78 lbs. / gal. / 333 gm/l
Applied (4:1+ M148)	
Flat	4.25 lbs. / gal. / 509 gm/l
Eggshell	4.08 lbs. / gal. / 489 gm/l
Semi-gloss	3.65 lbs. / gal. / 437 gm/l

Film build per coat

Applied 4:1 1.5 – 2.0 mils

Square foot coverage at 1 mil

Applied 4:1 (Spot)	813.1 sq. ft. / gal., no loss
Applied 4:1 (Overall)	823.3 sq. ft. / gal., no loss

Limitations

OmnTM AU and OmnTM SV should not be combined with components of other product lines

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320.

Material Safety Data Sheet:

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG Omni Distributor.

For additional information regarding this product, see the MSDS and label information.